

**airo-chemie**

A. Schmiemann GmbH & Co. KG
chemisch-technische Produkte
D-40736 Langenfeld · Postfach 1143
D-40764 Langenfeld · Carl-Leverkus-Str. 27
Tel. (02173) 8538-0 · Fax 853860 + 853870


V2 1401 EN

Technical Data Sheet - Product Information


Product: **FELGENSILBER**

**Characteristics:**

Fast drying acrylic lacquer for refurbishing old wheels.
Homogenous silver effect, resistant against abrasion, excellent rust protection.
The propellant is free of CFC (chlorofluorocarbon)

**Range of application:**

Car-finishing, industrial and private purpose

**Instructions for use:**

Clean surface from dust, grease and rust.
Remove loose paint layers. Old lacquer should be sanded.

Prior to application shake the spray can thoroughly for at least 1 to 2 minutes.

Apply 1 to 2 layers crosswise and homogeneously and keep a spraying distance of 25-30 cm.

Drying time at 20°C: around 15 minutes for a film thickness of 30 µ

Special indication: to avoid a decrease of the spray pressure
shake the spray can between the application steps

Chemical basis:

FELGENSILBER: acrylic resin, aluminium powder and solvents.
Propellant: propane / butane.

Temperature conditions:

Surrounding and material temperature should range between +18 °C and +20 °C.
Do not apply at temperatures lower than +15 °C.

Storage stability:

12 months in tightly closed tins when kept at +20 °C.

Disposal consideration:

Disposal according to local regulations.

Please consider our technical advice – be it verbally, in writing or testing and supplied to the best of our knowledge – as information only and without responsibility in respect to other parties. It does not release you from your obligation to test the products supplied regarding their suitability for the intended application. Handling and utilization of our products by the customer exceed our responsibility and are at the customer's liability. We guarantee that our products conform to their specification and we will refund or replace non conforming products only. Airo cannot be held responsible for any damages or accidents in connection with the use of our product.